



English

INSTRUCTIONS FOR USE:

TempSpan® CMT Temporary Cement

TempSpan CMT Temporary Cement is a eugenol-free resin cement formulated with sodium fluoride, potassium nitrate, and calcium phosphate to aid in the prevention of postoperative sensitivity during the provisional phase.

Indications

- Cementation of temporary crowns, bridges, inlays, and onlays.
- Trial seating of definitive restorations.

Contraindications

- Permanent cementation of definitive restorations.
- Temporary cementation of provisional veneers.

Cementing the provisional restoration

- 1a. Prior to placing the mixing tip, observe the level of *TempSpan* CMT Temporary Cement in the adjoining orifices. If the level is not the same in both orifices, bleed excess material from the syringe until both sides flow evenly. The mixing tip may now be effectively placed on the syringe.
- 1b. After dispensing material through the mixing tip, do not retract the plunger to stop the flow of material. Doing so can contaminate the base and catalyst causing material to cure in the syringe. To stop the flow of material through the mixing tip orifice, remove the used mixing tip and replace it with the storage cap.
2. Using slight pressure, dispense a thin layer of *TempSpan* CMT Temporary Cement directly into the provisional restoration.
3. Within 1 – 1½ minutes from initial mixing, carefully, but firmly, seat the provisional restoration on the preparation site.
4. Instruct the patient to gently occlude into the provisional until the restoration is fully seated.
5. Clean any excess *TempSpan* CMT Temporary Cement with a cotton swab prior to setting. Set cement may be removed with an explorer.
6. *TempSpan* CMT Temporary Cement will set in approximately 2½ - 3 minutes.

Working Characteristics

Mixing Ratio (base:catalyst)	1:1
Mixing Time	Auto-Mix
Working Time on Pad (Maximum)	1 - 1½ Minutes
Setting Time Intra-oral (from start of mix)	2½ - 3 Minutes

Storage

Refrigeration required. Store material between 36°F - 55°F (2°C - 12°C). Use at room temperature.

Refills

<i>TempSpan</i> CMT Temporary Cement	
1 - 4.5ml/6.9gm 1:1 Syringe	REF N69CA
Mixing Tips, Instructions & MSDS	

Mixing Tips	
50 - 1:1 Mixing Tips	REF N33CA
100 - 1:1 Mixing Tips	REF N33C

Wallingford, CT 06492 USA
tel: 203.265.7397



CEpartner4U, 3951DB; 13. NL.
tel: +31 (0)6.516.536.26